

Plain flexible rubber magnet



Width(mm)	Thickness(mm)	Length(m)	Surface	Pull strength(g/cm2)
610-1000	0.3	30/50/60	Plain	12
610-1000	0.4	15/20/30/50/60		16
610-1000	0.5	15/20/30/50/60		23
610-1000	0.75	10/15/20		38
610-1000	1	10/15/20		42
610-700	1.5	10/15		56
610-700	2	10		60

Magnetic property	Magnetic property Value							
	Br \geq		Hcb \geq		Hcj \geq		BH(max) \geq	
	mT	Gs	KA/m	Oe	KA/m	Oe	KJ/m ³	MGOe
Isotropic	185	1850	112	1400	147	1850	5.97	0.75
Anisotropic	245	2450	167	2100	195	2450	11.54	1.45

Note: Our isotropic flexible rubber magnet is available in the above dimensions.(Customized dimension is also available upon request.)